DuploCOLL® 200

Art. No. 11 00 09

Environmentally friendly double-sided adhesive tape with special paper carrier

Product construction				
	Name	Colour	Thickness [mm]	
Liner	Silicone paper	brown	approx. 0,08	
Adhesive covered side	Dispersion acrylic			
Carrier	Special paper	white	approx. 0,15	
Adhesive open side	Dispersion acrylic			
		Total thickness:	approx. 0,23	

Product advantages

- Tested and recognized according to UL 969
- Excellent initial adhesion (tack) and cohesion
- Good resistance to ageing and UV-radiation
- The outstanding viscoelastic adhesive formulation makes it particularly suitable for coarsepored material surfaces

Main application fields

- Self-adhesive preparation of plastics, metal, paper, ceramics, textile, foam and felt
- Used in the manufacture of carpet trims

Product features		Applicability on	
Initial adhesion	• • •	Foam	• • •
Final adhesion	• • 0	Rubber	• • 0
Dimensional stability	• • 0	Fabric	• • •
Adhesion on even surfaces	• • •	Glass/Ceramics	• • 0
Adhesion on rough surfaces	• • •	Wood	• • 0
Ageing resistance	• • •	High energy plastics: PVC, PC, ABS,	• • •
Weathering resistance	• • 0	Low energy plastics: PE, PP,	• • 0
Chemical resistance	• 0 0	Metal	• • •
Resistance to plasticizers	• 0 0	Paper/Cardboard	• • •
• • verv suitable • • o suitable	● ○ ○ suitable with reductions	○ ○ ○ not suitable	




DuploCOLL® 200

Art. No. 11 00 09

Environmentally friendly double-sided adhesive tape with special paper carrier

Specific technical data*	
Temperature range Temperature range under stress	-40 °C to +120°C -40 °C to +70 °C**
Fogging value reflectometric in accordance with DIN 75201, method A Fogging value gravimetric in accordance with DIN 75201, method B Odour value in accordance with VDA 270 after 24 h storage at room temperature	98,9 % < 0,2 mg not bothering



^{*} Specific test results, statistically not approved.

** Reached temperature in a rising heat test according to the internal test method PM-211 following DIN EN 1943 at 0,5 kg strength, beginning at 30 °C, increasing of temperature every 30 minutes by 10 °C.



DuploCOLL® 200

Art. No. 11 00 09

Environmentally friendly double-sided adhesive tape with special paper carrier

Technical Data			1
Shear strength	on steel according to DIN EN 1943, edition 1996, at +23 °C +/- 2°C	9 N/625 mm²	₩ 👍
Peel strength	on steel according to DIN EN 1939, edition 1996, at +23 °C +/- 2°C	30 N/25 mm	· III

Application	
Recommended application temperature	18 °C to 35 °C
Application guidelines	www.lohmann-tapes.com

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %). The storage stability is one year after delivery.

Product presentation					
Converted product	Rolls				
Width [mm]	> 6	> 10	> 19		
Length [m]	50	100	200		
Max. log width: 1500 mm	Other dimens	ions, die-cuts and	sheets on reques		

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

The physical characteristics contained in our data sheets represent typical or average values. They do not represent any warranties or guarantees and must not be used for technical specification purposes. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. The buyer is responsible for determining the suitability of the specific tape for its intended use in connection with user's method of application. Please consult our Technical Applications Department for specific advice. Our general Term and Conditions of Sale apply, particularly with regard to warranty and liability.

Date of issue: June 2011

Lohmann GmbH & Co. KG Irlicher Strasse 55 56567 Neuwied Germany

Phone: + 49 (0) 26 31 34 - 0 Fax: + 49 (0) 26 31 34 - 6661 E-mail: info@lohmann-tapes.com

For further Information www.lohmann-tapes.com

